COLLEGE


COLLEGE Naval 17


COLLEGE Anis 62


COLLEGE Poussin 20

COLLEGE Ficelle 09

COLLEGE Nacre 04


COLLEGE Naturel 26

COLLEGE acier 18


COLLEGE Noir 10


COLLEGE Corail 14

COLLEGE Framboise 81


COLLEGE Marine 25


COLLEGE Gentiane 16


COLLEGE Turquoise 53


COLLEGE Vert 24


COLLEGE Mastic 48

COLLEGE Blanc 01


COLLEGE Souris 31


COLLEGE Moka 13


COLLEGE Mordoré 133

COLLEGE Paille 83

sotexpro

(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected

COLLEGE

COLLEGE Pêche 52


COLLEGE Safran 49

COLLEGE Havane 44


COLLEGE Sanguine 05

COLLEGE Bergamotte 121

COLLEGE Olive 61


COLLEGE Absinthe 132

COLLEGE Indigo 144


COLLEGE Titanium 98

sotexpro

(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected

COLLEGE Evêque 154

This light-filtering fabric is available in a range of several colours, providing you with some great decoration possibilities.

Technical properties

Flame retardant Thermal

Applications Roman blinds - Panel curtains - Curtains - Decorative frames

Composition 100% FR polyester

Weight 200 g/m² **Width** 140 cm / 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↕ cm

Maintenance advice

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) metter(s)

Technical characteristics

Flame retardant	M1 / EN13773 : 2003 Class 1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno	
Optical index	Light reflexion :	**21 %**
	Light absorption :	**71 %**
	Light transmission :	**8 %**
Thermal index	Solar reflexion :	**43 %**
	Solar absorption :	**35 %**
	Solar transmission :	**22 %**
	UV transmission :	**8 %**
	Gtot :	**Gt 43 % Fc 73 %**
Resilience	Lightfastness (units Class/8)	**6**
	Dimentional Stability (%)	
	Warp	**-2.5**
	Weft	**-0.5**
	Breaking Elongation	
	Warp	**23**
	Weft	**24**
	Breaking load (daN)	
	Warp	**93**
	Weft	**120**