




COLLIOURE




COLLIOURE Olive 61




COLLIOURE Agrume 69




COLLIOURE Miel 17




COLLIOURE Mandarine
93




COLLIOURE Océan 91




COLLIOURE Pervenche
13




COLLIOURE Ardoise 08




COLLIOURE Glacier 43




COLLIOURE Souris 31




COLLIOURE Blanc 01



COLLIOURE Ivoire 02




COLLIOURE Naturel 26



COLLIOURE Brun 23




COLLIOURE Titanium 98




COLLIOURE Noir 12




COLLIOURE eucalyptus
117




COLLIOURE navy 120



COLLIOURE lin 11



COLLIOURE marine 25




COLLIOURE
Bergamotte 121



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected


COLLIOURE




COLLIOURE Absinthe
132




COLLIOURE Saumon
143




COLLIOURE Tomette 60



COLLIOURE Terre 107



COLLIOURE Aubergine
27




COLLIOURE Cacao 168



COLLIOURE Chataigne
55



COLLIOURE Chamois
111





COLLIOURE Pêche 52



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



COLLIOURE Arctique 58

This plain twill fabric comes in a range of several colours.

Technical properties



Flame retardant






Thermal

Applications Roman blinds - Panel curtains - Valences - Curtains - Cushions - Decorative frames

Composition 100% FR polyester

Weight 270 g/m² **Width** 140 cm / 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant	M1 / EN13773 : 2003 Class 1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno
Optical index	Light reflexion : 64 %
	Light absorption : 19 %
	Light transmission : 17 %
Thermal index	Solar reflexion : 64 %
	Solar absorption : 17 %
	Solar transmission : 19 %
	UV transmission : 3 %
	Gtot : Gt 36 % Fc 61 %
Resilience	Lightfastness (units Class/8) 6
	Dimensional Stability (%)
	Warp -3
	Weft -0.5
	Breaking Elongation
	Warp 26
	Weft 28
	Breaking load (daN)
Warp 100	
Weft 160	



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected