

COLLIOURE



COLLIOURE Olive 61



COLLIOURE Agrume 69



COLLIOURE Miel 17




COLLIOURE Mandarine
93




COLLIOURE Océan 91




COLLIOURE Pervenche
13




COLLIOURE Ardoise 08




COLLIOURE Glacier 43




COLLIOURE Souris 31




COLLIOURE Blanc 01




COLLIOURE Ivoire 02




COLLIOURE Naturel 26



COLLIOURE Brun 23




COLLIOURE Titanium 98




COLLIOURE Noir 12




COLLIOURE eucalyptus
117




COLLIOURE navy 120



COLLIOURE lin 11



COLLIOURE marine 25




COLLIOURE
Bergamotte 121



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected


COLLIOURE




COLLIOURE Absinthe
132




COLLIOURE Arctique 58



COLLIOURE Saumon
143




COLLIOURE Tomette 60



COLLIOURE Terre 107




COLLIOURE Aubergine
27



COLLIOURE Cacao 168



COLLIOURE Chamois
111




COLLIOURE Pêche 52



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



COLLIOURE Chataigne 55

This plain twill fabric comes in a range of several colours.

Technical properties



Flame retardant





Thermal

Applications Roman blinds - Panel curtains - Valences - Curtains - Cushions - Decorative frames

Composition 100% FR polyester

Weight 270 g/m² **Width** 140 cm / 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice   

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant

M1 / EN13773 : 2003 Class 1 / B1 / IMO PASS / UNI 8456 / 9174
Classe Uno

Optical index

Light reflexion : **64 %**

Light absorption : **19 %**

Light transmission : **17 %**

Thermal index

Solar reflexion : **64 %**

Solar absorption : **17 %**

Solar transmission : **19 %**

UV transmission : **3 %**

Gtot : **Gt 36 % Fc 61 %**

Resilience

Lightfastness (units Class/8) **6**

Dimensional Stability (%)

Warp **-3**

Weft **-0.5**

Breaking Elongation

Warp **26**

Weft **28**

Breaking load (daN)

Warp **100**

Weft **160**



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected