COLLIOURE


COLLIOURE Olive 61


COLLIOURE Agrume 69

COLLIOURE Miel 17


COLLIOURE Mandarine 93


COLLIOURE Océan 91


COLLIOURE Pervenche 13


COLLIOURE Ardoise 08


COLLIOURE Glacier 43


COLLIOURE Souris 31

COLLIOURE Blanc 01


COLLIOURE Ivoire 02


COLLIOURE Naturel 26


COLLIOURE Brun 23


COLLIOURE Titanium 98


COLLIOURE Noir 12


COLLIOURE eucalyptus 117

COLLIOURE navy 120

COLLIOURE marine 25


COLLIOURE Bergamotte 121


COLLIOURE Absinthe 132

sotexpro

(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected

COLLIOURE

COLLIOURE Arctique 58


COLLIOURE Saumon 143


COLLIOURE Tomette 60


COLLIOURE Terre 107

COLLIOURE Aubergine 27


COLLIOURE Cacao 168


COLLIOURE Chataigne 55


COLLIOURE Chamois 111


COLLIOURE Pêche 52

sotexpro

(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected

COLLIOURE lin 11

This plain twill fabric comes in a range of several colours.

Technical properties

Flame retardant

Thermal

Applications Roman blinds - Panel curtains - Valences - Curtains - Cushions - Decorative frames

Composition 100% FR polyester

Weight 270 g/m² **Width** 140 cm / 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↕ cm

Maintenance advice

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) metter(s)

Technical characteristics

Flame retardant	M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno	
Optical index	Light reflexion :	**64 %**
	Light absorption :	**19 %**
	Light transmission :	**17 %**
Thermal index	Solar reflexion :	**64 %**
	Solar absorption :	**17 %**
	Solar transmission :	**19 %**
	UV transmission :	**3 %**
	Gtot :	**Gt 35 % Fc 61 %**
Resilience	Lightfastness (units Class/8)	**6**
	Dimentional Stability (%)	
	Warp	**-3**
	Weft	**-0.5**
	Breaking Elongation	
	Warp	**26**
	Weft	**28**
	Breaking load (daN)	
	Warp	**100**
	Weft	**160**