

NATTE




NATTE bpi 00



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



NATTE bpi 00

This light-filtering fabric serves as a print medium.

Technical properties




Flame retardant

Applications Roman blinds - Panel curtains - Bedspreads - Valences - Bed runners - Curtains - Cushions

Composition 100% FR polyester

Weight 230 g/m² **Width** 140 cm

Fabric direction Standard Direction **Fitting** ↔ 0,0 cm ↓ 0,0 cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 25 linear(s) meter(s)

Technical characteristics

Flame retardant	M1 / IMO PASS		
Acoustic	Noise reduction coefficient (NRC) :	0.90	
Optical index	Light reflexion :	5 %	
	Light absorption :	94 %	
	Light transmission :	1 %	
Thermal index	Solar reflexion :	39 %	
	Solar absorption :	48 %	
	Solar transmission :	13 %	
	UV transmission :	0 %	
	Gtot :	Gt 48 % Fc 69 %	
Resilience	Lightfastness (units Class/8)	5	
	Pilling	5	
	Dimensional Stability (%)	Warp	-2
		Weft	-1
	Martindale (Cycles)	40000	
	Breaking Elongation	Warp	38
		Weft	21
	Breaking load (daN)	Warp	150
		Weft	93



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected