

SIENTO LITO



SIENTO LITO Minéral
157



SIENTO LITO Poireau
162



SIENTO LITO Lichen 156



SIENTO LITO Brousse
192



SIENTO LITO Cordage
172



SIENTO LITO Sahara
169



SIENTO LITO Hortensia
134



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



SIENTO LITO Lin 11

Light-filtering fabric made from recycled yarns

Technical properties



Flame retardant



Recycled fabrics

Applications Roman blinds - Panel curtains - Curtains - Decorative frames

Composition 80% recycled polyester FR / 20% polyester FR

Weight 330 g/m² **Width** 290 cm

Fabric direction Room High Direction **Fitting** ↔ cm ↓ cm

Maintenance advice    

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 Recyclé (CQ 1006/2)

Minimum order 1 linear(s) meter(s)

Technical characteristics

| | |
|-----------------|---|
| Flame retardant | M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno |
| Acoustic | Noise reduction coefficient (NRC) : 0.76 |
| | Weighted sound absorption coefficient (a _w) : 0.70 |
| | Acoustic absorption class (a _w) : C |
| Optical index | Light reflexion : 48 % |
| | Light absorption : 41 % |
| | Light transmission : 11 % |
| Thermal index | Solar reflexion : 55 % |
| | Solar absorption : 25 % |
| | Solar transmission : 20 % |
| | UV transmission : 2 % |
| | Gtot : Gt 39 % Fc 67 % |
| | |
| Resilience | Lightfastness (units Class/8) 5 |
| | Pilling 1 |
| | Dimensional Stability (%) |
| | Warp -1 |
| | Weft -0.5 |
| | Martindale (Cycles) 20000 |
| | Breaking Elongation |
| | Warp 49 |
| | Weft 34 |
| | Breaking load (daN) |
| | Warp 140 |
| Weft 79 | |



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on supports selected