




3141 bpi 00
Printing support



JUANA Fiesta 131
Print pattern



Printing support 3141 bpi 00 Print pattern JUANA Fiesta 131

Sheer fabric support for digital printing.

Technical properties



Flame retardant Transparent

Applications Roman blinds - Panel curtains - Curtains

Composition polyester/polyester FR

Weight 50 g/m²

Width 290 cm

Fabric direction Room High Direction

Fitting ↔ 20.0 cm ↓ 20.0 cm

Maintenance advice     

Label France Terre Textile / OEKO-TEX STANDARD 100

Minimum order 25 linear(s) meter(s)



Visual not taking into account the printing medium, the final rendering may vary according to the chosen medium.

Technical characteristics

Flame retardant	M1 / B1 / IMO PASS																				
Optical index	<table border="0"> <tr> <td>Light reflexion :</td> <td>25 %</td> </tr> <tr> <td>Light absorption :</td> <td>4 %</td> </tr> <tr> <td>Light transmission :</td> <td>71 %</td> </tr> </table>	Light reflexion :	25 %	Light absorption :	4 %	Light transmission :	71 %														
Light reflexion :	25 %																				
Light absorption :	4 %																				
Light transmission :	71 %																				
Transparent veil	Yes																				
Thermal index	<table border="0"> <tr> <td>Solar reflexion :</td> <td>25 %</td> </tr> <tr> <td>Solar absorption :</td> <td>3 %</td> </tr> <tr> <td>Solar transmission :</td> <td>72 %</td> </tr> <tr> <td>UV transmission :</td> <td>65 %</td> </tr> <tr> <td>Gtot :</td> <td>Gt 50 % Fc 85 %</td> </tr> </table>	Solar reflexion :	25 %	Solar absorption :	3 %	Solar transmission :	72 %	UV transmission :	65 %	Gtot :	Gt 50 % Fc 85 %										
Solar reflexion :	25 %																				
Solar absorption :	3 %																				
Solar transmission :	72 %																				
UV transmission :	65 %																				
Gtot :	Gt 50 % Fc 85 %																				
Resilience	<table border="0"> <tr> <td>Lightfastness (units Class/8)</td> <td>6</td> </tr> <tr> <td>Dimensional Stability (%)</td> <td></td> </tr> <tr> <td> Warp</td> <td>-1</td> </tr> <tr> <td> Weft</td> <td>0</td> </tr> <tr> <td>Breaking Elongation</td> <td></td> </tr> <tr> <td> Warp</td> <td>28</td> </tr> <tr> <td> Weft</td> <td>34</td> </tr> <tr> <td>Breaking load (daN)</td> <td></td> </tr> <tr> <td> Warp</td> <td>30</td> </tr> <tr> <td> Weft</td> <td>36</td> </tr> </table>	Lightfastness (units Class/8)	6	Dimensional Stability (%)		Warp	-1	Weft	0	Breaking Elongation		Warp	28	Weft	34	Breaking load (daN)		Warp	30	Weft	36
Lightfastness (units Class/8)	6																				
Dimensional Stability (%)																					
Warp	-1																				
Weft	0																				
Breaking Elongation																					
Warp	28																				
Weft	34																				
Breaking load (daN)																					
Warp	30																				
Weft	36																				