



# BELORA Taupe 95

This plain dimout fabric comes in a range of several colours. It does not have an M1 fire rating.

## Technical properties



Thermal



Acoustic

Applications Roman blinds - Lining - Curtains

Composition 100% polyester

Weight 260 g/m<sup>2</sup> Width 290 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice     

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 30 linear(s) meter(s)

## Technical characteristics

|                 |   |                        |
|-----------------|---|------------------------|
| Flame retardant | NF 12952  |                        |
| Acoustic        | Noise reduction coefficient (NRC) :                       | <b>0.88</b>            |
|                 | Weighted sound absorption coefficient (a <sub>w</sub> ) : | <b>0.90</b>            |
|                 | Acoustic absorption class (a <sub>w</sub> ) :             | <b>A</b>               |
| Optical index   | Light reflexion :   | <b>3 %</b>             |
|                 | Light absorption :  | <b>97 %</b>            |
|                 | Light transmission :                                      | <b>0 %</b>             |
| Thermal index   | Solar reflexion :   | <b>27 %</b>            |
|                 | Solar absorption :  | <b>73 %</b>            |
|                 | Solar transmission :                                      | <b>0 %</b>             |
|                 | UV transmission :   | <b>0 %</b>             |
|                 | Gtot :  | <b>Gt 48 % Fc 81 %</b> |
| Resilience      | Lightfastness (units Class/8)                             | <b>4</b>               |
|                 | Dimensional Stability (%)                                 |                        |
|                 | Warp  | <b>0</b>               |
|                 | Weft  | <b>0</b>               |
|                 | Breaking Elongation                                       |                        |
|                 | Warp  | <b>17</b>              |
|                 | Weft  | <b>27</b>              |
|                 | Breaking load (daN)                                       |                        |
|                 | Warp  | <b>87</b>              |
|                 | Weft  | <b>110</b>             |



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60  
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on supports selected