

BORA Perle 96

This plain fabric with shiny backing will enhance comfort levels in the premises by providing optimal protection against light radiation.

Technical properties







Thermal

Applications Roman blinds - Lining - Curtains

Composition 100% FR polyester

Weight 260 g/m² Width 280 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice     

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant	B1 / IMO PASS	
Optical index	Light reflexion :	51 %
	Light absorption :	49 %
	Light transmission :	0 %
Thermal index	Solar reflexion :	50 %
	Solar absorption :	50 %
	Solar transmission :	0 %
	UV transmission :	0 %
	Gtot :	Gt 41 % Fc 69 %
Resilience	Lightfastness (units Class/8)	5



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected