



# BOREAL Faience 149

This fabric comes in a range of several colours. It meets all styles and atmospheres.

## Technical properties



Flame retardant



Thermal



Acoustic

Applications Roman blinds - Valences - Lining - Bed runners - Curtains

Composition 100% FR polyester

Weight 260 g/m<sup>2</sup> Width 290 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice     

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

## Technical characteristics

Flame retardant	M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno
Acoustic	Noise reduction coefficient (NRC) : <b>0.88</b> Weighted sound absorption coefficient (a <sub>w</sub> ) : <b>0.90</b> Acoustic absorption class (a <sub>w</sub> ) : <b>A</b>
Optical index	Light reflexion : <b>55 %</b> Light absorption : <b>45 %</b> Light transmission : <b>0 %</b>
Thermal index	Solar reflexion : <b>53 %</b> Solar absorption : <b>47 %</b> Solar transmission : <b>0 %</b> UV transmission : <b>0 %</b> Gtot : <b>Gt 40 % Fc 67 %</b>
Resilience	Lightfastness (units Class/8) <b>6</b> Dimensional Stability (%) Warp <b>0</b> Weft <b>0</b> Breaking Elongation Warp <b>17</b> Weft <b>27</b> Breaking load (daN) Warp <b>87</b> Weft <b>110</b>



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60  
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on supports selected