



NOCTURNE MURA 2334 Ivoire 115

False plain design printed on our blackout Nocturne, the Mura design is inspired by the asperities and shades of a wall aged by time as to create a subtle material effect.

Technical properties



Flame retardant



Thermal

Applications Roman blinds - Panel curtains - Lining - Curtains

Composition 100% polyester with white flocked acrylic backing

Weight 280 g/m² Width 280 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice     

Minimum order 1 linear(s) meter(s)

Technical characteristics

| | | | |
|-----------------|-------------------------------------|-----------------|------|
| Flame retardant | M1 / BS 5867 TYPE C / B1 / IMO PASS | | |
| Optical index | Light reflexion : | 71 % | |
| | Light absorption : | 29 % | |
| | Light transmission : | 0 % | |
| Thermal index | Solar reflexion : | 66 % | |
| | Solar absorption : | 34 % | |
| | Solar transmission : | 0 % | |
| | UV transmission : | 0 % | |
| | Gtot : | Gt 35 % Fc 60 % | |
| Resilience | Lightfastness (units Class/8) | 4 | |
| | Pilling | 3-4 | |
| | Dimensional Stability (%) | Warp | -0.5 |
| | | Weft | 0 |
| | Martindale (Cycles) | 40000 | |
| | Breaking Elongation | Warp | 19 |
| | | Weft | 22 |
| | Breaking load (daN) | Warp | 37 |
| | | Weft | 57 |



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected