



# NOCTURNE Sapin 126

This blackout fabric is very efficient. It is available in a wide range of colors

## Technical properties



Flame retardant



Thermal

**Applications** Roman blinds - Panel curtains - Lining - Curtains

**Composition** 100% polyester with white flocked acrylic backing

**Weight** 280 g/m<sup>2</sup> **Width** 280 cm

**Fabric direction** Room high or standard direction **Fitting** ↔ cm ↓ cm

**Maintenance advice**    

**Minimum order** 1 linear(s) meter(s)

## Technical characteristics

|                 |                                     |                 |
|-----------------|-------------------------------------|-----------------|
| Flame retardant | M1 / BS 5867 TYPE C / B1 / IMO PASS |                 |
| Optical index   | Light reflexion :                   | 71 %            |
|                 | Light absorption :                  | 29 %            |
|                 | Light transmission :                | 0 %             |
| Thermal index   | Solar reflexion :                   | 66 %            |
|                 | Solar absorption :                  | 34 %            |
|                 | Solar transmission :                | 0 %             |
|                 | UV transmission :                   | 0 %             |
|                 | Gtot :                              | Gt 35 % Fc 60 % |
| Resilience      | Lightfastness (units Class/8)       | 5               |
|                 | Pilling                             | 3-4             |
|                 | Dimentional Stability (%)           |                 |
|                 | Warp                                | -0,5            |
|                 | Weft                                | 0               |
|                 | Martindale (Cycles)                 | 40000           |
|                 | Breaking Elongation                 |                 |
|                 | Warp                                | 19              |
|                 | Weft                                | 22              |
|                 | Breaking load (daN)                 |                 |
|                 | Warp                                | 37              |
|                 | Weft                                | 57              |



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60  
(Showroom) Le LAB' SOTEXPRO - 4 rue du Mail - 75002 PARIS - FRANCE

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected