



SADYNA Ivoire 115

This plain, twill, light-filtering fabric is a classic. Perfect for simpler designs or to coordinate with our woven Jacquard patterns. Available in several colours.

Technical properties



Flame retardant



Thermal



Acoustic

Applications Decorative frames - Roman blinds - Panel curtains - Valences - Bed runners - Curtains - Cushions

Composition 100% FR polyester

Weight 320 g/m² **Width** 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)



Technical characteristics

| | |
|-----------------|--|
| Flame retardant | M1 / B1 / IMO PASS |
| Acoustic | Noise reduction coefficient (NRC) : 0.88 Weighted sound absorption coefficient (a _w) : 0.85 Acoustic absorption class (a _w) : B |
| Optical index | Light reflexion : 59 % Light absorption : 28 % Light transmission : 13 % |
| Thermal index | Solar reflexion : 63 % Solar absorption : 20 % Solar transmission : 17 % UV transmission : 4 % Gtot : Gt 37 % Fc 62 % |
| Resilience | Lightfastness (units Class/8) 6 Pilling 2-3 Dimensional Stability (%) Warp -1.5 Weft 0 Martindale (Cycles) 20000 Breaking Elongation Warp 24 Weft 22 Breaking load (daN) Warp 150 Weft 160 |



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected