COLLEGE


COLLEGE Naval 17


COLLEGE Anis 62


COLLEGE Poussin 20

COLLEGE Ficelle 09

COLLEGE Nacre 04


COLLEGE Naturel 26

COLLEGE acier 18


COLLEGE Noir 10


COLLEGE Corail 14

COLLEGE Framboise 81


COLLEGE Marine 25


COLLEGE Gentiane 16


COLLEGE Vert 24


COLLEGE Mastic 48

COLLEGE Blanc 01


COLLEGE Souris 31


COLLEGE Moka 13

COLLEGE Mordoré 133


COLLEGE Paille 83

COLLEGE Pêche 52

sotexpro

(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected

COLLEGE


COLLEGE Safran 49

COLLEGE Havane 44


COLLEGE Sanguine 05

COLLEGE Evêque 154

COLLEGE Bergamotte 121

COLLEGE Olive 61


COLLEGE Absinthe 132

COLLEGE Indigo 144


COLLEGE Titanium 98

sotexpro

(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



COLLEGE Turquoise 53

Cette toile pare-solaire se décline autour d'une gamme de plusieurs coloris, vous offrant de grandes possibilités de décoration

Propriétés techniques

Non feu Thermique

Applications Store bateau - Parois japonaises - Rideaux - Décoration murale

Composition 100% polyester FR

Poids 200 g/m² **Laize** 140 cm / 280 cm

Sens Contre sens ou sens normal **Raccord** ↔ cm ↕ cm

Conseils d'entretien

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum commande 1 mètre(s) linéaire(s)

Caractéristiques techniques

Non feu	M1 / EN13773 : 2003 Class 1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno	
Indices optiques	Réflexion lumière :	**21 %**
	Absorption lumière :	**71 %**
	Transmission lumière :	**8 %**
Indices thermiques	réflexion solaire :	**43 %**
	absorption solaire :	**35 %**
	Transmission solaire :	**22 %**
	Transmission UV :	**8 %**
	Gtot :	**Gt 43 % Fc 73 %**
Résistance	Solidité lumière (unités Class/8)	**6**
	Stabilité dimensionnelle (%)	
	Chaîne	**-2.5**
	Trame	**-0.5**
	Allongement rupture (mm)	
	Chaîne	**23**
	Trame	**24**
	Résistance rupture (daN)	
	Chaîne	**93**
	Trame	**120**